

TwinTopEvo

Natural Discs + Micro-granulate = Safety²



Twin Top® Evo is the advanced version of Amorim's popular Twin Top® technical stopper, aimed at the popular premium segment, with high-grade natural cork discs at both ends and a micro-agglomerate cork body. It is ideal for wines with floral and fruity notes, recommended to be stored in the bottle for up to 36 months. The individually moulded micro-agglomerate cork body assures higher homogeneity and greater physical and mechanical resistance.

Only the finest natural cork is used to produce this elegant technical stopper, which is subjected to rigorous quality control procedures, including Amorim's patented ROSA Hi-Tech® treatment—thus delivering a high-performance stopper that guarantees an exceptional level of sensorial neutrality.

SPECIFICATIONS

| TESTS | CHARACTERISTICS | SPECIFICATIONS |
|-------------------------------|--------------------------------|-----------------|
| | | |
| | LENGTH (I) | l ± 1,0 mm |
| DIMENSIONAL | DIAMETER (d) | d ± 0,4 mm |
| | OVALISATION | ≤ 0,3 mm |
| | SPECIFIC WEIGHT | 250 — 330 Kg/m³ |
| PHYSICAL MECHANICAL | MOISTURE | 4% — 9% |
| MECHANICAL | EXTRACTION FORCE | 20 — 40 daN |
| | PEROXIDE CONTENT | ≤ 0,1 mg/cork |
| CHEMICAL | DUST CONTENT (1) | ≤ 3 mg/cork |
| | 2,4,6 — TRICHLOROANISOLE (TCA) | ≤ 0,5 ng/L* |
| | 12 MONTHS | 1,20 mg of O2 |
| OTR (OXYGEN TRANSFER RATE) | 24 MONTHS | 1,29 mg of O2 |
| | 36 MONTHS | 1,34 mg of O2 |

⁽¹⁾ This characteristic is only applicable to cork stoppers with surface treatment. Test methods are internal, having as a guiding line NP 2803 norm (Cork stoppers – Physical Assays) part 1 to 7.

PRODUCTION FLOWCHART

GRINDING

THIN CORK BARK

GRANULES

DISCS

NOSA HIGH TECH®

INOS II SYSTEM

MOULDING

ELECTRONIC SORTING

GLUING

MECHANICAL FINISHES

WASHING

SORTING

TREATMENT

PACKAGING AND SHIPPING

STANDARD DIMENSIONS

44 x 24 mm

FOOD STANDARDS

All Amorim & Irmãos, S.A. products comply with existing regulations and legislation (European and FDA — Food and Drug Administration) for products in contact with food.













U.I. Amorim Distribuição

U.I. Amorim Distribuiç U.I. PTK U.I. Champcork U.I. Top Series U.I. Equipar U.I. De Sousa

VERSION 03/2016 www.amorimcork.com | marketing.ai@amorim.com

RECOMMENDATIONS TO THE USER

_

SELECTION AND STORAGE OF CORK

Amorim can calculate the required cork diameter by studying the internal profile of the bottleneck, the characteristics of the wine and the corking conditions.

Order your cork stoppers for immediate use. These cork stoppers should be used within six months of the date of manufacture if the storage conditions are respected.

Store the cork stoppers in their original packages, in a well-ventilated room with controlled temperature between 15°C and 25°C and 50% to 70% humidity.

Do not leave boxes and/or bags open with surplus cork stoppers.

CORKING CONDITIONS

Ensure any dust its removed before corking.

Ensure the cork is compressed smoothly, to a diameter no less than 15,5 mm.

Ensure insertion of the cork is a quick as possible.

For standard bottlenecks, the cork should be inserted to 1 mm below the top of the neck.

Minimise moisture on the inside of the bottleneck.

Headspace should be at least 15 mm at 20°C.

Don't leave the cork stoppers in the feeder as to avoid dust

Always use stoppers with a surface treatment suitable for the type of beverage, bottling process and selected bottle.

A vacuum must be created in order to prevent internal pressures.

FOUIPMENT MAINTENANCE

Maintain the corker jaws free of nicks and signs of wear.

Ensure proper alignment of plunger and location ring.

Ensure corking machine operates smoothly, especially during compression.

Clean all cork-handling surfaces regularly with chlorine-free products.

Ensure the equipment is suited to the cork and bottle used.

STORAGE AND TRANSPORT OF WINE

After bottling, the bottles should be kept in an upright position for at least 10 minutes.

Ideal bottle storage conditions are 12°-18°C at 50-70% humidity.

Keep the wine cellar free of insects.

Bottles should be transported in an upright position.

The product must not be stored in a location exposed to sunlight, heated environment and in direct contact with the ground.

Please always check the most updated version of the technical sheet of the product you are using as the manufacturer reserves its right to implement product changes without prior notice.

^{*} Average value and according to the method specified by the ISO20752 norm